



Jiaxing Selected Technology Co., Ltd.

PRODUCT: BIO UNDERWATER LIFT BAG LB1680

Item	Test method	Unit	Test value
Support Cloth	DIN ISO 2076		100%PES
Total Weight	DIN EN ISO 2286-2	g/m2	1680
Width	DIN EN ISO 2286-1	cm	205,250,300,320
Thickness	DIN EN ISO 2286-2	mm	1.12
Tensile strength Warp	DIN 53354	N/5cm	10000
Tensile strength Weft	DIN 53354	N/5cm	8800
Tear strength Warp	DIN 53363	N	1800
Tear strength Weft	DIN 53363	N	1600
Adhesion Strength	DIN 53357	N/5cm	220
Temperature Resistance	BS 3424 Method 10		-30℃ /+70℃
Environmental Protective	REACH/Rohs		
Lacquering (optional)	Acrylic		
UV RESISTANT	2500 hours		
Flame retardant	Available as request		
Application	UNDERWATER LIFT BAG		

These indicated technical data are based on average results. actual data 's tolerance +-5%.Due to production procedures slight deviations can occur.All technical data are in accordance with the present standard of knowledge and give product information without legal binding.All data apply to new products

Company : Jiaxing Selected Technology Co., Ltd.

Ad : No.1, Fenghuang dongyuan,Dingqiao,Haining,Zhejiang.China. 314413

Email: admin@selectedfabric.com

Website: www.selectedfabric.com